

PRODUCTION OF WHITE POLYETHYLENE TEREPHTHALATE FILM

Patent number: JP62207337
Publication date: 1987-09-11
Inventor: NAGATA RYUICHI; YOSHII TOSHIYA; ASAKURA MASAYOSHI
Applicant: TORAY INDUSTRIES
Classification:
- **international:** B29C55/12; B29K67/00; B29L7/00; C08J5/18;
C08K3/32; C08K5/51; C08L67/02
- **european:**
Application number: JP19860049303 19860306
Priority number(s): JP19860049303 19860306

Report a data error here

Abstract of JP62207337

PURPOSE: To obtain the titled film which has no bubbles and is useful as a substrate for photographic paper, labels, display board, white board, X-ray intensifying screen, etc., by melt-extruding a mixture of polyethylene terephthalate, pulverized calcium carbonate and a phosphorus compd. and biaxially orienting the film. **CONSTITUTION:** 100pts.wt. polyethylene terephthalate (A) composed of at least 80mol% of ethylene terephthalate units, 5-25pts.wt. pulverized calcium carbon ate (B) having an average particle size of 0.1-4μ, a degree of whiteness of not lower than 80% and an impurity content of not higher than 10%, and 0.005-1pt.wt. phosphorus compd. (C) such as phosphorous acid, phosphoric acid and allyl or alkyl phosphates, etc. are thoroughly dried and then mixed with one another in a mixer, etc. to obtain a mixture. The mixture is fed to an extruder heated to 260-290 deg.C and melt-extruded through a T-die. The resulting unoriented film is simultaneously oriented in the lengthwise and widthwise directions 2-5 times at a drawing temp. of 80-130 deg.C. If desired, the oriented film is thermally set at 150-235 deg.C for 1-60sec to obtain the titled film.

Data supplied from the **esp@cenet** database - Worldwide